

Exaton 19.13.4.L

Exaton 19.13.4.L is a chromium-nickel-molybdenum strip electrode used for electro-slag welding (ESW) or submerged arc welding (SAW) to deposit a second layer corrosion resistant alloy of 19%Cr/13%Ni/4%Mo composition on carbon- and low alloyed steels.

The buffer layer is deposited using an over-alloyed consumable, such as 21.13.3.L, 22.11.L or 24.13.L

Классификации	SFA/AWS A5.9 : EQ317L EN ISO 14343-A : B 19 13 4 L
----------------------	---

Хим. состав проволоки									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	Ferrite FN
<=0.02	1.5	0.4	<=0.020	<=0.020	14	19	3.6	<=0.3	7