

## OK Autrod 308H

A continuous solid corrosion resisting chromium-nickel wire for welding of austenitic chromium nickel alloys of 18% Cr - 8% Ni-type.

OK Autrod 308H has a good general corrosion resistance. The alloy has a high carbon content which makes this alloy suitable for applications used at higher temperatures. The alloy is used in chemical and petrochemical plants for welding of pipes, cyclones and boilers.

<b>Классификации</b>	AWS A5.9 : ER308H EN ISO 14343-A : G 19 9 H
----------------------	--

<b>Тип сплава</b>	Austenitic 19% Cr - 9% Ni - High C
<b>Защитный газ</b>	M12, M13 (EN ISO 14175)

### Хим. состав проволоки

C	Mn	Si	Ni	Cr	N	Nb	FN WRC-92
0.05	1.9	0.5	9.2	19.8	0.06	0.01	9

### Данные наплавки

Диаметр	Ток	В	Скорость подачи проволоки	Кэфф. наплавки
0.8 mm	50-140 A	16-22 V	3.4-11.0 m/min	0.8-2.7 kg/h
1.0 mm	80-190 A	16-24 V	2.9-8.4 m/min	1.1-3.1 kg/h
1.2 mm	180-280 A	20-28 V	4.9-8.5 m/min	2.6-4.5 kg/h