

OK Tigrod NiCu-7 (старое название OK Tigrod 19.93)

Bare nickel based welding rods alloyed with 30 % Cu for welding of base materials of the same type. Can also be used to join these alloys to steel. The weld metal has good resistance to flowing seawater and has high strength and toughness over a rather wide temperature range. Has also good resistance to hydrofluoric acid, sulfuric acid, alkalis etc. Can be used for welding of similar types of base materials which are age-hardenable with small additions of Ti and Al.

Классификации	AWS A5.14 : ERNiCu-7 EN ISO 18274 : S Ni 4060 (NiCu30MnTi)
Тип сплава	Alloyed nickel (Ni + 30 % Cu + 2 % Ti + 2 % Fe)
Защитный газ	I1 (EN ISO 14175)

Механические свойства при растяжении

Состояние	Предел текучести	Предел прочности при растяжении	Удлинение
После сварки	300 MPa	520 MPa	35 %

Хим. состав наплавленного металла

C	Mn	Si	S	P	Ni	Al	Cu	Nb	Ti
0.01	3.2	0.06	0.001	0.001	64	0.1	30	0.002	1.8

Хим. состав наплавленного металла

Fe	Nb+Ta	Ta
0.7	0.005	0.003

Хим. состав проволоки

C	Mn	Si	Ni	Al	Cu	Ti	Fe	Nb+Ta
0.03	3	0.3	64	0.03	28	2	2	< 0.5